

# RR355-60-CR

## Resin for General Purpose

- Strong & Durable
- Fast curing
- Cost effective
- Excellent surface finish



Ideal for high clarity and dimensionally challenging builds. Its low viscosity with excellent re-wetting provide fast stunning clear parts for industrial applications.

## Mechanical Properties

Tensile Strength	ASTM D638	52 Mpa
Tensile Modulus	ASTM D638	2500 Mpa
Elongation at break	ASTM D638	6-10%
Flexural Strength	ASTM D790	82 Mpa
Flexural Modulus	ASTM D790	2000 Mpa
Impact Strength	ASTM D256	21.4 J/m
Notched Izod	ASTM D256	0.4 ft-lb/in
Hardness	ASTM D2240	83 shore D
Water Absorbtion	ASTM D570-98	0.25%
Heat Deflection @ 66 psi	ASTM D648	55 deg C
Heat Deflection @ 264 psi	ASTM D648	50 deg C